

MATERIAL PROPERTY DATA SHEET




EroNet™ C125®

Long Term • Double Net • Coconut Matrix •
Erosion Control Blanket

DESCRIPTION

C125 consists of a machine produced, clean coconut fiber matrix, manufactured for consistent coverage and thickness. The coconut matrix is confined by a UV stabilized photodegradable, synthetic net on top and bottom, mechanically (stitch) bound on two-inch centers. C125 is intended for slope or channel erosion control applications requiring up to thirty-six months of functional longevity. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



C125 is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

Material Content

Matrix	Coconut		
Netting	Top and Bottom Net: Medium weight, Synthetic, Regular Degradable	Double Net (black)	
Thread	Synthetic, Regular Degradable		

Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	56.3 lb (25.6 kg)	563 lb (256.0 kg)
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)

Material available in custom roll sizes

Approvals & Classification

Classification	FHWA: Type 4.B / ECTC: Type 4.B	
TTI Approvals	Class 1 Type B, D	Class 2 Type E,F
NTPEP Number	ECP-2020-01-012	

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2022, North American Green is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.

Index Property Test Method Typical

Thickness	ASTM D6525	0.28 in. (7 mm)
Mass/Unit Area	ASTM D6566	9.0 oz/sy (305 g/sm)
Tensile Strength – MD	ASTM D6818	280 lbs/ft (4.1 kN/m)
Tensile Strength – TD	ASTM D6818	180 lbs/ft (2.6 kN/m)
Elongation - MD	ASTM D6818	25%
Elongation – TD	ASTM D6818	25%
Density/Specific Gravity	D792	N/A
Light Penetration	ASTM D6567	15%
Biomass Improvement	ASTM D7322	500%
Water Absorption	ASTM D1117	300%

Design Parameters

Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.02	N/A
Slope Maximum Gradient ¹	1H:1V	N/A
Permissible Shear Stress ²	2.3 psf (110 Pa)	N/A
Permissible Velocity ²	9.0 fps (2.7 m/s)	N/A

Manning's n Roughness (HEC-15)

τ_{lower}	τ_{mid}	τ_{upper}
0.033	0.031	0.031

- 1 Maximum Gradient a recommendation for typical insllations.
- 2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.
- 3 Vegetated values dependent on established stand of vegetation



Rev. 4.2023
Scan for additional and updated product information, or [click here](#).

