

ACF LS125N: Super Grade

Woven Geotextile for Silt Fence Applications

ACF LS125N is a woven polypropylene geotextile that has been stabilized to resist degradation due to ultraviolet exposure and is resistant to commonly encountered mildew, insects and soil chemicals, and is non-biodegradable. Polypropylene is stable with a pH range of 2 to 13.

Geotextile Property	Test Method	Minimum Average Roll Values
Grab Tensile Strength	ASTM D4632	124 x 124 Lbs
Grab Tensile Elongation	ASTM D4632	15 %
Trapezoid Tear Strength	ASTM D4533	65 x 65 Lbs
CBR Puncture Strength	ASTM D6241	350 Lbs
UV Resistance @ 500 Hours	ASTM D4355	80 %
AOS	ASTM D4751	30 Sieve
Permittivity (sec ⁻¹)	ASTM D4491	0.1 sec ⁻¹
Flow Rate	ASTM D4491	10 gpm/ft ²

Results quoted above are the mean of multiple tests conducted at an independent testing facility. ACF LS125N meets or exceeds values listed.

Packaging

Roll Width	24, 36, 42, or 48 in.
Roll Length	100-7800 ft.

11 2024

Disclaimer: Ferguson/ACF Environmental assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information