

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506











Material and Performance Specification

ECSC-3™ Straw/Coconut Turf Reinforcement Mat

Description:

The ECSC-3™ is made with uniformly distributed 70% agricultural straw, 30% coconut fiber and three polypropylene nets securely sewn together with UV stabilized thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECSC-3™ is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels. The ECSC-3™ meets Type 5.A, 5.B and 5.C specification requirements established by the Erosion Control Technology Council (ECTC).

Matrix:		1		2		
	709	% Straw	309	% Coconut		
Netting:	Туре				Net Color	
Top:	: Medium weight 8# PMSF UV Stabilized Polypropylene		d Polypropylene		Black	
Middle:	Heavyweight 24# PMS	F UV Stabilized	Polypropylene			
Bottom:	Medium weight 8# PM	SF UV Stabilize	d Polypropylene			
Net Opening:		Тор		Middle	Bottom	
	0.5" x 0.5"		0.	4" x 0.5"	0.5" x 0.5"	
Thread:		Туре		Color		
	UV Stabilized Thread			Black		
Roll Sizes:	St	andard	ш	A" Size	Mega	
Width:	8 ft	2.4 m	4.00 ft	t 1.2 m	16 ft 4.9 m	
Length:	112.5 ft	34.3 m	225 ft	t 68.6 m	112.5 ft 34.3 m	
Weight:*	92 lbs	41.7 kg	92 II	os 41.7 kg	184 lbs 83.5 kg	
Area:	100 yd ²	83.6 m ²	100 y	d² 83.6 m²	200 yd² 167.2 m²	
#/Pallet:		9		9	9	

^{*}Weight at time of manufacturing within specified tolerances.

Index Value Properties*:						
Property	Test Method		T	「ypical		
Mass/Unit Area	ASTM D6566	14.00	oz/yd²	474.7 g/m2		
Thickness	ASTM D6525	0.39	in	9.91 mm		
Tensile Strength-MD	ASTM D6818	728	lb/ft	10.62 kN/m		
Elongation-MD	ASTM D6818	21	%			
Tensile Strength-TD	ASTM D6818	632	lb/ft	9.22 kN/m		
Elongation-TD	ASTM D6818	20.8	%			
Light Penetration	ASTM D6567	7	%			
Density / Specific Gravity	ASTM D792	0.919	g/cm³			
Water Absorption	ASTM D1117	259	%			
Resiliency	ASTM D6524	N/A	%			
UV Resistance	ASTM D4355	80	%	500 hours		

^{*}May differ depending upon raw material variations

Slope Performance Design Values*:						
Property	Test Me	Value				
C-Factors	ASTM D	0.00				
Slope Length (L)	≤ 3:1	3:1-2:1	≥ 2:1			
< 50 ft (15 m)	0.001	0.005	0.070			
50 ft – 100 ft	0.010	0.018	0.078			
>100 ft (30 m)	0.020	0.032	0.080			

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=18.16	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=17.83	
	150mm (6in) / hr-30 min	SLR**=17.50	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	3.40 lb/ft ²	

ECTC Method 4 Germination Top soil; Fescue; 21 day incubation 497 %

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:							
Property	Test Method	Valu					
Unvegetated Shear Stress	ASTM D 6460	3.00	lbs/ft ²	143.64	Pa		
Unvegetated Velocity	ASTM D 6460	11.0	ft/s	3.35	m/s		
Vegetated Shear Stress	ASTM D 6460	10.0	lbs/ft ²	478.80	Pa		
Vegetated Velocity	ASTM D 6460	20.0	ft/s	6.10	m/s		
Manning's N (Value Represents a Range)			0.02	24			

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

^{*}Bench scale tests should not be used for design purposes.

^{**}Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor