

MATERIAL PROPERTY DATA SHEET



EXCEL CS-3™


Extended Term • Double Net • Coconut/Straw Matrix • Erosion Control Blanket

DESCRIPTION

The Coconut/Straw Excel CS-3 extended term Erosion Control Blanket consists of 30% coconut fibers and 70% weed free agricultural straw manufactured into a continuous matrix. The coconut/straw matrix is confined by a photodegradable, synthetic net on top and bottom, mechanically (stitch) bound on two-inch centers. Excel CS-3 is intended for applications requiring up to twenty-four months of functional longevity. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.

Each roll of Excel CS-3 is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

CS-3 has replaced ECSC-2, formerly provided by East Coast Erosion. CS-3 meets or exceeds the ECSC-2 and can be used as a replacement with no limitations.



Material Content	
Matrix	Straw/ Coconut Blend
Netting	Top Net: Medium weight, Synthetic, Regular Degradable
	Bottom Net: Lightweight, Synthetic, Regular Degradable
Thread	Synthetic, Regular Degradable

Standard Roll Sizes			
Width	8 ft (2.4 m)	16 ft (4.9 m)	
Length	112 ft (34.1 m)	563 ft (171.0 m)	
Weight ± 10%	53 lb (24.1 kg)	530 lb (241.0 kg)	
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)	

Material available in custom roll sizes

Approvals & Classification	
Classification	FHWA: Type 3.B / ECTC: Type 3.B
TTI Approvals	Class 2 Type E
NTPEP Number	ECP-2022-01-013

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, Western Excelsior is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.



Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.30 in.	(8 mm)
Mass/Unit Area	ASTM D6566	8.5 oz/sy	(290 g/sm)
Tensile Strength – MD	ASTM D6818	150 lbs/ft	(2.2 kN/m)
Tensile Strength – TD	ASTM D6818	130 lbs/ft	(1.9 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	25%	
Density/Specific Gravity	D792	N/A	
Light Penetration	ASTM D6567	12%	
Biomass Improvement	ASTM D7322	500%	
Water Absorption	ASTM D1117	350%	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.03	N/A
Slope Maximum Gradient ¹	2H:1V	N/A
Permissible Shear Stress ²	2.0 psf (95 Pa)	N/A
Permissible Velocity ²	8.0 fps (2.4 m/s)	N/A

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.045	0.036	0.031

1 Maximum Gradient a recommendation for typical installations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Rev. 4.2023

Scan for additional and updated product information, or [click here](#).



MATERIAL PROPERTY DATA SHEET




EXCEL CS-3 All Natural™

Extended Term • Double Net • Coconut/Straw Matrix • Biodegradable • Erosion Control Blanket

DESCRIPTION

Excel CS-3 All Natural (CS-3AN) Extended Term Erosion Control Blanket consists of 30% coconut fibers and 70% weed free agricultural straw manufactured into a continuous matrix. The coconut/straw matrix is confined by a biodegradable, jute/scrim net on top and bottom, mechanically (stitch) bound on two-inch centers with a biodegradable, cotton thread. Excel CS-3AN is intended for slope and channel erosion control applications requiring up to twenty-four months of functional longevity. The material is fully degradable. The net, thread, and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



Each roll of Excel CS-3AN is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

CS-3AN has replaced ECSC-2B, formerly provided by East Coast Erosion. CS-3AN meets or exceeds the ECSC-2B and can be used as a replacement with no limitations.

Material Content

Matrix	Straw/Coconut Blend		
Netting	Top & Bottom Net: Jute Scrim, Biodegradable, Leno Weave	Double Net	
Thread	Biodegradable Cotton or Rayon		

Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	53 lb (24.1 kg)	530 lb (241.0 kg)
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)

Material available in custom roll sizes

Approvals & Classification

FHWA/ECTC Class	Type 3.B
TTI Approvals	Class 2 Type E
NTPEP Number	ECP-2020-01-010

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, Western Excelsior is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.



Index Property Test Method Typical

Thickness	ASTM D6525	0.30 in. (8 mm)
Mass/Unit Area	ASTM D6566	8.5 oz/sy (290 g/sm)
Tensile Strength – MD	ASTM D6818	210 lbs/ft (3.1 kN/m)
Tensile Strength – TD	ASTM D6818	190 lbs/ft (2.8 kN/m)
Elongation - MD	ASTM D6818	15%
Elongation – TD	ASTM D6818	15%
Density/Specific Gravity	D792	N/A
Light Penetration	ASTM D6567	12%
Biomass Improvement	ASTM D7322	500%
Water Absorption	ASTM D1117	350%

Design Parameters

Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.03	N/A
Slope Maximum Gradient ¹	2H:1V	N/A
Permissible Shear Stress ²	2.1 psf (100 Pa)	N/A
Permissible Velocity ²	8.0 fps (2.4 m/s)	N/A

Manning's n Roughness (HEC-15)

τ_{lower}	τ_{mid}	τ_{upper}
0.045	0.036	0.031

¹ Maximum Gradient a recommendation for typical insllations.

² Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

³ Vegetated values dependent on established stand of vegetation

Rev. 4.2023

Scan for additional and updated product information, or [click here](#).

